

## **TECHNICAL BULLETIN**

**PRODUCT:** POLYRAD FM12-45

POLYRAD FM12-45 is a specially formulated multifunctional urethane acrylate/methacrylate oligomer formulated for use in many radcure applications. POLYRAD FM12-45 combines acrylate and methacrylate functionality to yield a medium hardness oligomer that exhibits fast cure. It provides excellent adhesion to a variety of substrates, including porcelain, glass, polycarbonate, stainless steel, titanium, and most metal alloys. Excellent chemical resistance, high clarity and excellent scratch resistance characterize formulations based on POLYRAD FM12-45.

### **FEATURES:**

- Fast cure response
- Medium hardness
- Excellent scratch resistance
- Excellent optical properties
- Good exterior durability
- Resistant to yellowing and other degradative effects from exposure to sunlight
- Excellent color retention
- Excellent adhesion properties

### **RECOMMENDED USES:**

POLYRAD FM12-45 is a unique radcure oligomer recommended for abrasion-resistant protective coatings, adhesives, and inks. Applications include abrasion resistant protective finishes, automotive/transportation finishes, optical hardcoats, and decorative applications. It is also recommended for any hard surface requiring abrasion resistance and chemical resistance.

### **PHYSICAL PROPERTIES:**

Density (g/cm <sup>3</sup> )	1.1250 ± 0.0125
Non-volatile, by weight	>99.9%
Molecular weight	980 ± 30
Viscosity (Haake RT20, 10 rpm @ 40°C)	40000 ± 500 centipoise
Shrinkage (TGA @ 300°C)	< 1.0%
Color (APHA)	< 100
Appearance	Clear, colorless
Free NCO (ppm on solids)	<0.1 max.



### **TYPICAL FILM PROPERTIES:**

Clear films were prepared by initiating with 0.5 parts by weight methylbenzylformate (MBF) and irradiating with UV energy at 1400-1500 millijoules/cm<sup>2</sup>:

Tensile Strength	9500 ± 250 psi.	
% Elongation	8.5 ± 0.5%	
Pencil Hardness	3H min.	
60° Gloss	>88 min.	
MEK Double Rubs	>300	
Cross-Hatch Adhesion:		Scale: 0 = total adhesion failure
Porcelain	5	1 = more than 75% failure
Stainless Steel	5	2 = more than 50% failure
Copper	5	3 = more than 25% failure
Titanium	5	4 = up to 25% failure
Brass	5	5 = no adhesion failure
Glass	5	
Polycarbonate	5	

For further information, please direct your inquiries to:

Designer Molecules Inc.  
10090 Willow Creek Road  
San Diego, CA 92131

Contact: Sharon Hanson  
Phone: (858) 536-4703  
Fax: (858) 348-1123  
E-mail: [shanson@designermoleculesinc.com](mailto:shanson@designermoleculesinc.com)  
Web page: [www.designermoleculesinc.com](http://www.designermoleculesinc.com)